



Performance Pigments & Colors

FERRO (FRANCE) SARL
43, RUE JEANNE D'ARC
52115 SAINT-DIZIER CEDEX
FRANCE

TEMPERATURE-TABLE for PTCR
Higher quality products and lower costs through improved, reliable firing control

Type PTCR - ZTH	Ring Colour : White/Beige
Ferro no. : 1425250	Dimensions : ± 20 x 10 x 7,0 mm
Temperature Range °C : 560 - 660°C	

Ring dia-meter	Ring tempe-rature	Ring dia-meter	Ring tempe-rature	Ring dia-meter	Ring tempe-rature	Ring dia-meter	Ring tempe-rature	Ring dia-meter	Ring tempe-rature	Ring dia-meter	Ring tempe-rature
mm	°C	mm	°C	mm	°C	mm	°C	mm	°C	mm	°C
		20,14	558	19,64	621	19,14	654				
		20,13	561	19,63	622	19,13	655				
		20,12	563	19,62	622	19,12	656				
		20,11	565	19,61	623	19,11	657				
		20,10	567	19,60	624	19,10	658				
		20,09	570	19,59	624	19,09	659				
		20,08	572	19,58	625	19,08	659				
		20,07	574	19,57	625	19,07	660				
		20,06	576	19,56	626						
		20,05	578	19,55	626						
		20,04	579	19,54	627						
		20,03	581	19,53	627						
		20,02	583	19,52	628						
		20,01	585	19,51	629						
		20,00	586	19,50	629						
		19,99	588	19,49	630						
		19,98	589	19,48	630						
		19,97	591	19,47	631						
		19,96	592	19,46	631						
		19,95	594	19,45	632						
		19,94	595	19,44	633						
		19,93	596	19,43	633						
		19,92	598	19,42	634						
		19,91	599	19,41	634						
		19,90	600	19,40	635						
		19,89	601	19,39	636						
		19,88	602	19,38	636						
		19,87	604	19,37	637						
		19,86	605	19,36	638						
		19,85	606	19,35	638						
		19,84	607	19,34	639						
		19,83	608	19,33	640						
		19,82	608	19,32	640						
		19,81	609	19,31	641						
		19,80	610	19,30	642						
		19,79	611	19,29	643						
		19,78	612	19,28	643						
		19,77	613	19,27	644						
		19,76	613	19,26	645						
		19,75	614	19,25	646						
		19,74	615	19,24	646						
		19,73	616	19,23	647						
		19,72	616	19,22	648						
		19,71	617	19,21	649						
		19,70	618	19,20	650						
		19,69	618	19,19	650						
		19,68	619	19,18	651						
		19,67	620	19,17	652						
		19,66	620	19,16	653						
		19,65	621	19,15	654						

Powder Batch # : 004 prefired	Batch approved
Date : 07/10/2022	Quality Inspection :

For inquiries :
Customer Service Desk
Phone : +49 69 27116 432
Fax : +49 69 27116 243

