

TEMPERATURE-TABLE for PTCR

Higher quality products and lower costs through improved, reliable firing control

Type PTCR - HTH	Ring Colour	:	White
Vibrantz no. :	Dimensions	:	± 20 x 10 x 7,0 mm
Temperature Range °C :			1450 - 1750°C

Ring dia-meter	Ring temperature	Ring dia-meter	Ring temperature	Ring dia-meter	Ring temperature	Ring dia-meter	Ring temperature	Ring dia-meter	Ring temperature	Ring dia-meter	Ring temperature
mm	°C	mm	°C	mm	°C	mm	°C	mm	°C	mm	°C
		19,74	1450	19,24	1577	18,74	1651	18,24	1692	17,74	1736
		19,73	1453	19,23	1579	18,73	1652	18,23	1693	17,73	1737
		19,72	1455	19,22	1581	18,72	1653	18,22	1694	17,72	1738
		19,71	1458	19,21	1583	18,71	1654	18,21	1694	17,71	1739
		19,70	1461	19,20	1585	18,70	1655	18,20	1695	17,70	1740
		19,69	1464	19,19	1587	18,69	1656	18,19	1696	17,69	1741
		19,68	1467	19,18	1589	18,68	1657	18,18	1697	17,68	1742
		19,67	1469	19,17	1591	18,67	1658	18,17	1697	17,67	1743
		19,66	1472	19,16	1593	18,66	1659	18,16	1698	17,66	1744
		19,65	1475	19,15	1595	18,65	1660	18,15	1699	17,65	1745
		19,64	1478	19,14	1596	18,64	1661	18,14	1700	17,64	1747
		19,63	1481	19,13	1598	18,63	1662	18,13	1701	17,63	1748
		19,62	1483	19,12	1600	18,62	1662	18,12	1701	17,62	1749
		19,61	1486	19,11	1602	18,61	1663	18,11	1702	17,61	1750
		19,60	1489	19,10	1603	18,60	1664	18,10	1703		
		19,59	1492	19,09	1605	18,59	1665	18,09	1704		
		19,58	1494	19,08	1607	18,58	1666	18,08	1705		
		19,57	1497	19,07	1608	18,57	1667	18,07	1705		
		19,56	1500	19,06	1610	18,56	1668	18,06	1706		
		19,55	1503	19,05	1612	18,55	1668	18,05	1707		
		19,54	1505	19,04	1613	18,54	1669	18,04	1708		
		19,53	1508	19,03	1615	18,53	1670	18,03	1709		
		19,52	1511	19,02	1616	18,52	1671	18,02	1709		
		19,51	1513	19,01	1618	18,51	1672	18,01	1710		
		19,50	1516	19,00	1619	18,50	1672	18,00	1711		
		19,49	1519	18,99	1621	18,49	1673	17,99	1712		
		19,48	1521	18,98	1622	18,48	1674	17,98	1713		
		19,47	1524	18,97	1624	18,47	1675	17,97	1714		
		19,46	1526	18,96	1625	18,46	1676	17,96	1715		
		19,45	1529	18,95	1626	18,45	1676	17,95	1715		
		19,44	1531	18,94	1628	18,44	1677	17,94	1716		
		19,43	1534	18,93	1629	18,43	1678	17,93	1717		
		19,42	1536	18,92	1630	18,42	1679	17,92	1718		
		19,41	1539	18,91	1632	18,41	1679	17,91	1719		
		19,40	1541	18,90	1633	18,40	1680	17,90	1720		
		19,39	1544	18,89	1634	18,39	1681	17,89	1721		
		19,38	1546	18,88	1636	18,38	1682	17,88	1722		
		19,37	1549	18,87	1637	18,37	1682	17,87	1723		
		19,36	1551	18,86	1638	18,36	1683	17,86	1724		
		19,35	1553	18,85	1639	18,35	1684	17,85	1725		
		19,34	1556	18,84	1640	18,34	1685	17,84	1725		
		19,33	1558	18,83	1641	18,33	1685	17,83	1726		
		19,32	1560	18,82	1643	18,32	1686	17,82	1727		
		19,31	1562	18,81	1644	18,31	1687	17,81	1728		
		19,30	1564	18,80	1645	18,30	1688	17,80	1729		
		19,29	1567	18,79	1646	18,29	1688	17,79	1730		
		19,28	1569	18,78	1647	18,28	1689	17,78	1731		
		19,27	1571	18,77	1648	18,27	1690	17,77	1732		
		19,26	1573	18,76	1649	18,26	1691	17,76	1733		
		19,25	1575	18,75	1650	18,25	1691	17,75	1734		

 Powder Batch # : 463
 Date : 13/05/2025

 Batch approved
 Quality Inspection : 

 For inquiries :
 Customer Service Desk
 Phone : +49 69 27116 432
 Fax : +49 69 27116 243
